



POLYESTER RESIN ACCELERATOR

Characteristics

Cobalt Octoate is a violet-blue colored, low viscosity liquid used in combination with MEK Peroxide for room temperature curing of unsaturated polyester resins. It is supplied in different concentrations varying from 1% to 12%.

Specifications

Appearance	violet-blue colored	
Form	Liquid	
Density (25°C)	0.9±0.004	kg/m ³
Cobalt metal content	1-12	%
Flash Point	39	°C

Storage

Cobalt octoate must be stored below 30°C, away from direct sunlight in closed containers.

Packaging

Available in 25kg and 5kg polyethylene containers.

(06/2004E-R00)

